SILICONE TURBO HOSE WITH ARAMID REINFORCEMENT

| This Data Sheet Covers | |
|---------------------------|------|
| the Following Hose Types: | TCH. |



Silflex Limited Coed Cae Lane , Pontyclun , Mid Glam , CF72 9HJ, UK Tel: +44 (0)1443 238464 Fax: +44 (0)1443 237781 www.samcosport.com e-mail: sales@samcosport.com

General Use

Samco®Sport turbo hose has been specifically designed for the demanding requirements of the motorsport and fast road car tuning markets. It meets or exceeds the requirements of SAE J20 R1 Class A. It is primarily designed for use in turbocharger systems. It can however be used in many other applications where the properties of silicone are preferable to those of other rubbers, where a flexible joint is required between rigid pipe work, or where higher working temperatures compared to standard silicone/polyester are required.

Working Temperature Range:-50°C to +250°C. (-58°F to +482°F)Working Pressures:Dependant on hose construction and customer requirements.

Construction

Plies of silicone, reinforced with Aramid fabric. The number of plies will vary depending on the working pressure, bore size, and required wall thickness. A galvanised spring steel wire helix may also be added for high or low-pressure applications, or where extra flexibility is required

Materials Specifications

Silicone Rubber Compound

| Colour | Various (R.I.O. as | | |
|---------------------------------------|--------------------|--|--|
| | Standard) | | |
| Hardness (IHRD) | 65 ± 5 | | |
| Specific Gravity (g/cm ³) | 1.18 ± 0.05 | | |
| Tensile Strength (Mpa) | 8.6 | | |
| Elongation at Break (%) | 308 | | |
| Tear Strength (KN/m) | 13 | | |

The above physical properties refer to a test sheet press cured for 5mins at 115°C, and post cured for 4 hrs @ 200°C. Tested to the relevant BS903 standard.

Fluid resistance figures can be supplied on request.

Knitted Aramid Fabric

| Description | Fine Mesh | | |
|---|--------------------------|--|--|
| Yarn Type | 100% Aramid | | |
| Finish | Scour & Set (with Resin) | | |
| Bursting Strength (Fabric) (7.98cm Dia. Ring) | 258 Kpa | | |
| Weight | 115g/cm ² | | |
| Extensibility at Burst | 25-35% | | |

Other Aramid fabrics are also available depending on the working parameters of the hose.

Spring Steel Wire Helix (where applicable)

Constructed from galvanised spring steel wire (to BS5216 HS3) at a spacing of 2-3 tpi, and buried between the plies.

Certificates Of Conformity

Certificates of conformity can be supplied with deliveries if required.

Page 1 of 2



Registered in England No. 2569811

Currie & Warner Group





WORKING PRESSURE GUIDELINES FOR SILICONE TURBO HOSE WITH ARAMID REINFORCEMENT

This Data Sheet Covers the Following Hose Types:

тсн

Silflex Limited Coed Cae Lane , Pontyclun , Mid Glam , CF72 9HJ, UK

Tel: +44 (0)1443 238464 Fax: +44 (0)1443 237781 www.samcosport.com e-mail: sales@samcosport.com

| I.D. | | Number Vall Of Plies (mm) | Burst pressure | | Recommended Max. Working Pressure @ 4:1 safety Factor | | |
|--------|----------|------------------------------|----------------|--------------------|---|-------|-------|
| (mm) | (") | | (11111) | (Psi) | (Bar) | (Psi) | (Bar) |
| 6.5mm | 1/4" | 3 | 4mm | 818 | 56.4 | 204.5 | 14.1 |
| 8mm | 5/16" | 3 | 4mm | 677 | 46.7 | 169.3 | 11.7 |
| 9.5mm | 3/8" | 3 | 4mm | 580 | 40.0 | 145.0 | 10.0 |
| 11mm | 7/16" | 3 | 4mm | 508 | 35.0 | 127.0 | 8.8 |
| 12.7mm | 1/2" | 3 | 4mm | 437 | 30.1 | 109.3 | 7.5 |
| 16mm | 5/8" | 3 | 4mm | 361 | 24.9 | 90.3 | 6.2 |
| 19mm | 3/4" | 3 | 4mm | 309 | 21.3 | 77.3 | 5.3 |
| 22mm | 7/8" | 3 | 4mm | 270 | 18.6 | 67.5 | 4.7 |
| 25mm | 1" | 3 | 4mm | 241 | 16.6 | 60.3 | 4.2 |
| 28mm | 1 1/8" | 3 | 4mm | 218 | 15.0 | 54.5 | 3.8 |
| 30mm | 1 3/16" | 3 | 4mm | 205 | 14.1 | 51.3 | 3.5 |
| 32mm | 1 1/4" | 3 | 4mm | 193 | 13.3 | 48.3 | 3.3 |
| 35mm | 1 3/8" | 3 | 4mm | 177 | 12.2 | 44.3 | 3.1 |
| 38mm | 1 1/2" | 3 | 4mm | 165 | 11.4 | 41.3 | 2.9 |
| 41mm | 1 5/8" | 4 | 4.8mm | 203 | 14.0 | 50.8 | 3.5 |
| 45mm | 1 3/4" | 4 | 4.8mm | 189 | 13.0 | 47.3 | 3.3 |
| 48mm | 1 7/8" | 4 | 4.8mm | 177 | 12.2 | 44.3 | 3.1 |
| 51mm | 2" | 4 | 4.8mm | 168 | 11.6 | 42.0 | 2.9 |
| 54mm | 2 1/8" | 4 | 4.8mm | 161 | 11.1 | 40.3 | 2.8 |
| 57mm | 2 1/4" | 4 | 4.8mm | 152 | 10.5 | 38.0 | 2.6 |
| 60mm | 2 3/8" | 4 | 4.8mm | 146 | 10.1 | 36.5 | 2.5 |
| 63mm | 2 1/2" | 4 | 4.8mm | 141 | 9.7 | 35.3 | 2.4 |
| 65mm | 2 9/16" | 5 | 5.5mm | 170 | 11.7 | 42.5 | 2.9 |
| 68mm | 2 11/16" | 5 | 5.5mm | 162 | 11.2 | 40.5 | 2.8 |
| 70mm | 2 3/4" | 5 | 5.5mm | 160 | 11.0 | 40.0 | 2.8 |
| 76mm | 3" | 5 | 5.5mm | 148 | 10.2 | 37.0 | 2.6 |
| 80mm | 3 1/8" | 5 | 5.5mm | 144 | 9.9 | 36.0 | 2.5 |
| 83mm | 3 1/4" | 5 | 5.5mm | 138 | 9.5 | 34.5 | 2.4 |
| 89mm | 3 1/2" | 5 | 5.5mm | 131 | 9.0 | 32.8 | 2.3 |
| 102mm | 4" | 5 | 5.5mm | 116 | 8.0 | 29.0 | 2.0 |
| 110mm | 4 1/3" | 5 | 5.5mm | 107 | 7.4 | 26.8 | 1.9 |
| 114mm | 4 1/2" | 5 | 5.5mm | 103 | 7.1 | 25.8 | 1.8 |
| 127mm | 5" | 5 | 5.5mm | 94 | 6.5 | 23.5 | 1.6 |
| 152mm | 6" | 5 | 5.5mm | 81 | 5.6 | 20.3 | 1.4 |
| 200mm | 8" | 5 | 5.5mm | 64 TCH bosos in | 4.4 | 16.0 | 1.1 |

This data applies to all standard TCH hoses in the Samco Sport range.

DS006



Registered in England No. 2569811